



Head Office
 Red Deer, Alberta
 Phone: 403-314-2221
 Fax: 403-314-2226
 Web Site: www.hpc.ca

9091

9:1

DTM (Direct to Metal) Polyurethane Enamel

Material Description

A self priming modified aliphatic polyurethane, providing full gloss with excellent impact resistance and weatherability. Available in a wide range of custom colors.

Intended Applications

For use on industrial equipment and machinery, oil and gas process equipment, piperacks, storage tank exteriors, drilling and service equipment and structural steel.

Colors Available
Various colors available

Finish
Gloss 85+ @ 60 deg

Physical Properties

Resin System
Modified aliphatic urethane

Pigment System

Solvent System
Aliphatic and aromatic hydrocarbons

Packaged Viscosity
8.0+/-0.5 Poise @25C depending on color

Solids by Weight
53% depending on color

Solids by Volume
43% depending on color

Theoretical Coverage
approx 158 - 174 sq ft/L Depending on Color

Total VOC
500-550 g/L Depending on Color

Wet Film Thickness
4.0 - 8.0 mils

Dry Film Thickness
2.0 - 4.0 mils

Specific Gravity
0.96 - 1.12 depending on color

Dry to Touch *
30 minutes

Dry to Handle *
2 hours

Dry to Recoat *
Before 1 hour and after 24 hours

Coats Required
1-2

Components
2

Pot Life Hours
6 hours

Recommended Thinners
Xylene or TS-28 Slow Reducer

Use With
N/A

Additional Application Notes

* Times listed are at 25°C. Temperature and humidity will affect dry and recoat times.

Date Issued	20/04/2009	Supersedes	20/04/2004
--------------------	------------	-------------------	------------

The above information is given in good faith and to the best of our knowledge. Every reasonable precaution is taken in the manufacture of all products and compilation of data to ensure that they are consistent with the Manufacturer's standards. As the effectiveness of each product depends, in part, on correct methods of use and application, and since the conditions of the surface, application and method of use are beyond our control, no guarantee of such products or this data is made or implied by this. By virtue of this disclosure, it is the responsibility of the buyer to satisfy itself of the suitability of the goods for its own particular process and it will be deemed to have done so by virtue of accepting the goods on this understanding.



Head Office
 Red Deer, Alberta
 Phone: 403-314-2221
 Fax: 403-314-2226
 Web Site: www.hpc.ca

9091 **9:1**
DTM (Direct to Metal) Polyurethane Enamel

Required Surface Preparation and Application Parameters

Surface Preparation	Surfaces must be free of dirt, grease, and oil. Steel surfaces must be thoroughly cleaned, a minimum SSPC SP-3 power tool cleaning is required. SSP - SP6 Commercial Blast Cleaning is Preferred.		
Atmospheric Conditions	Surface and product temperatures must be at least 10 deg C (50 F) and at least 3 deg C (5F) above dew point. Apply in dry weather when relative humidity is less than 85%.		
Blend Ratio	9 parts A 1 part B	Induction Period	15 minutes
Reduction	Airless (5-10%) / A.A. Airless (10-20%)		
Application Viscosity	Airless (28" Z #2) / A.A. Airless (24" Z #2)		
Force Cure	60 min @ 70 deg C (160F) after 30 min flash off		
Airless Pressure	1400-2000 PSI min at tip	Airless Tip Size	0.0011" - 0.015"
AA Airless Pressure	850 PSI min at tip	AA Airless Tip Size	0.009" - 0.013"
AA Airless Air Pressure	30 - 60 PSI		
Conventional Spray			
Brush	Polyester or nylon	Roller	Short nap
Procedure Part 1	Rinse all equipment with thinner prior to and after application.		
Procedure Part 2	When application is made by airless or air assisted airless, use and inbound pressure approx. 10-15 lbs above the level at which "fingering"		
Procedure Part 3	Special attention should be given to all edges, pits, welds, corners, rivets and other rough spots to insure complete coverage.		

Additional Information

Package Sizes	3.78 litres, 18.9 litres, 180 litres
Safety Information	See label precautions and MSDS.

Date Issued	20/04/2009	Supersedes	20/04/2004
--------------------	------------	-------------------	------------

The above information is given in good faith and to the best of our knowledge. Every reasonable precaution is taken in the manufacture of all products and compilation of data to ensure that they are consistent with the Manufacturer's standards. As the effectiveness of each product depends, in part, on correct methods of use and application, and since the conditions of the surface, application and method of use are beyond our control, no guarantee of such products or this data is made or implied by this. By virtue of this disclosure, it is the responsibility of the buyer to satisfy itself of the suitability of the goods for its own particular process and it will be deemed to have done so by virtue of accepting the goods on this understanding.